



ENDUTEX - REVESTIMENTOS TEXTEIS, SA

VIZELA / PORTUGAL



TECHNICAL DATA SHEET

REFERENCE: PRINT MS 55 FR

DESCRIPTION : PVC DOUBLE COATED HIGH TENACITY POLYESTER SCRIM

COMPOSITION : 67 % PVC
33 % POLYESTER

WIDTH : 137 - 160 - 320 - 500 cm

CHARACTERISTIC	SPECIFICATION	METHOD
THICKNESS (mm)	0.50	
TOTAL MASS (g/m ²)	350 ± 30	EN ISO 2286-2
FABRIC MASS (g/m ²)	115 ± 10	EN ISO 2286-2
BREAKING LOAD (daN/50mm)	L.: 130 T.: 170	EN ISO 1421
BREAKING EXTENSION (%)	L.: 17 T.: 21	EN ISO 1421
TEAR STRENGTH (daN)	L.: 20.0 T.: 16.0	DIN 53363
AVERAGE LIGHT TRANSMISSION	19.0	SF 600 Plus Spectrophotometer
AVERAGE PERMEABILITY OF FABRIC TO AIR (l/m ² /s)	950	EN ISO 9237
BURNING BEHAVIOUR	M2	NF P92-503
BURNING BEHAVIOUR	B1	DIN 4102

L – Along T - Across

NOTE : Unless otherwise stated, the figures presented shall be regarded as typical values for the material, and not as a minimum to be satisfied.

Date	Revision	QUALITY CONTROL	TECHNICAL MANAGER
2005.07.27	1		